



SPECTRALOCK® PRO Grout

SPECTRALOCK PRO Grout offers the high performance, color uniformity, durability and stain resistance of epoxy grout with extraordinary ease of use.

Globally Proven
Construction Solutions



FEATURES/BENEFITS

- Meets performance requirements of ANSI A118.3–1999.
- 80 minutes working time at 21°C.
- Inhibits the growth of stain-causing mold and mildew in the grout joints with Microban® antimicrobial product protection.
- Ideal for installations at wide temperature ranges.
- Uniform color —no blotchiness or shading.
- Easy to maintain, cleanable to the original color.
- Chemical resistant.
- Stain resistant.
- Tough, durable, and crack resistant.
- Outperforms cement based grout.
- Non-sag formula for walls and floors.
- High fashion with Dazzle component.

MANUFACTURER/ DISTRIBUTED BY

LATICRETE South East Asia Pte Ltd
No. 38 Sungei Kadut, Street 2 (Level 2, A3) Singapore 729245
Telephone: +65 6515 3028 Fax: +65 6515 3037
Internet: se.laticrete.com



USES

- Ceramic tile, glass tile and stone applications, residential and commercial.
- Interior and exterior.
- Floors and walls.
- Ideal for re-grouting applications.
- Swimming pools, fountains and other wet area applications.

STANDARDS/CERTIFICATIONS

- ANSI A118.3, American National Standard Specifications for Chemical Resistant, Water Cleanable Tile-Setting and -Grouting Epoxy and Water Cleanable Tile-Setting Epoxy Adhesive tested with 1244 Bright White
- ISO 13007-3
- BS EN 13888



This product has been certified green under the UL GREENGUARD Certification Program.

Packaging

Commercial Unit consists of:

Part A: 4 x 0.6kg

Part B: 4 x 0.6kg

Part C: 4 x 4.1kg / 8 x 2.05kg

Approximate Coverage

Refer to Coverage Chart.

Actual coverage will vary depending on job site conditions, actual tile size and installed grout joint size. Add 10% for waste, spillage and clean-up, and another 10%–15% when grouting unglazed quarry tile.

Shelf Life

Factory sealed containers of this product part A & B are guaranteed to be of first quality for one (1) year* if stored at temperatures greater than 0°C and less than 35°C.

* High humidity will reduce the shelf life of bagged product.

Limitations

- Not for use in areas subjected to harsh chemicals, or areas exposed to aggressive cleaning regimens (e.g. steam cleaning). Not for use on floor and base areas in veterinary clinics, kennels, or in applications exposed to high concentrations of food and mineral acids or areas exposed to high temperatures. For these areas LATICRETE recommends using grout that meets ANSI A118.5 such as LATAPOXY® 2000 Industrial Grout.
- Epoxy grout for ceramic tile and stone is not a replacement for a waterproofing membrane. When a waterproofing membrane is required, use a LATICRETE Waterproofing Membrane.
- Actual color shade, and texture may vary due to job site conditions, installation technique and raw material. The colors of cured material may not match and in some cases differ considerably between the actual colors achieved on site. No responsibility can be accepted once the products have been applied. Rest assures that essential controls are taken during the production of the product colors.
- Color and gloss retention of the coating finish may vary depending on type of color, subject to environmental exposures such as temperature, UV intensity, chemical spills, application quality and generic type of resinous finish. Contact LATICRETE Technical representative for further information.

Cautions

- DO NOT add water or any other material to the mixture, or re-temper with water. This will have an adverse effect on the product and void all warranties.
- Protect finished work from traffic until fully cured.
- SpectraLOCK®† PRO Grout liquid components might irritate eyes and skin. Avoid contact with eyes and/or prolonged contact with skin. Wear protective gear (gloves, long sleeve shirt, and safety glasses) when applying. Flush thoroughly with water in case of initial contact.

- DO NOT ingest internally. Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator or dust mask. See MSDS for more information.
- Keep out of reach of children.
- Protect from freezing.
- Light colors may darken and dark colors may fade slightly from direct UV exposure in exterior applications. Consult with LATICRETE Technical Services for specific exterior recommendations.
- SPECTRALOCK Dazzle (Glow) not for use in submerged installations.
- Maximum stain resistance is achieved in seven days at 21°C. Protect from exposure to acids (such as mustard, salad dressing, etc.) and strong cleaners during this period.
- Protect grout from dirt, construction debris, and contamination for 7 days @ 21°C.
- SPECTRALOCK PRO Grout is a sanded grout. Use of sanded grouts in joints <1/8" (3 mm) will result in a coarser surface compared to surfaces in wider joints.
- Some soft polished marble or delicate glazed or glass tile might be scratched by SPECTRALOCK PRO Grout during installation. Apply a small test area to determine results before grouting entire installation.
- SPECTRALOCK Dazzle (Glow) might discolor from strong alkali cleaners and acids. Use a neutral pH solution of soap and water when cleaning SPECTRALOCK PRO Grout mixed with SPECTRALOCK Dazzle (Glow).
- In steam rooms or submerged applications, allow SPECTRALOCK PRO Grout to cure for 10 days at 21°C days before use of area and filing with water. See TDS 192 for more information on these applications.
- In submerged underwater applications, please note that water balancing of PH, total alkalinity and calcium hardness is important to ensure durability of grout.
- SPECTRALOCK PRO Grout is resistant to staining when exposed to most household products and cleaners (e.g. ketchup). However, long term exposure to any material without proper cleaning and maintenance will increase the probability of stains.
- Epoxy Resins may affect the color of white or porous stones (such as White Carrara, Thasos White, Royal Danby etc.)

† United States Invention Patent No.: 6881768 (and other Patents)

TECHNICAL DATA

Performance Properties

Test	Test Method	Results
Water Cleanability	ANSI A118.3 E5.1	Water Cleanable at 80 minutes
Initial Set Service Strength	ANSI A118.3 E5.2	> 2 hours < 24 hours
Shrinkage	ANSI A118.3 E5.3	< 0.25%
Vertical Joint Sag	ANSI A118.3 E5.4	Pass
Shear Bond Strength @ 14 days	ANSI A118.3 E5.5	>6.8N/mm ²
Compressive Strength	ANSI A118.3 E5.6	>23N/mm ²

Tensile Strength	ANSI A118.3 E5.7	>7.5N/mm ²
Thermal Shock	ANSI A118.3 E5.8	>3.4N/mm ²
Water Absorption	ANSI A118.3	< 0.50%

Chemical Resistance* Chart

Chemical Name	Splash Exposure (30 min)	Intermittent Exposure (24 hours)	Continuous Exposure (7 days)
20 % Sulfuric Acid	R	R*	NR*
5 % Lactic Acid (Milk)	R	R	R
50 % Tannic Acid	R	R	R
10 % Oxalic Acid	R	R	R
5 % Acetic Acid (Vinegar)	R	R	R
5 % Benzoic Acid	R	R	R
3 % Formic Acid	R	R	NR
5 % Citric Acid (Gatorade Drink)	R	R	R
10 % Potassium Permanganate	R*	R*	R*
1 % Potassium Permanganate	R*	R*	R*
5 % Sodium Hypochlorite (Bleach)	R	R	NR
45 % KOH (Cascade)	R	R	R
Distilled Water	R	R	R

Chemical Resistance* Chart

Chemical Name	Splash Exposure (30 min)	Intermittent Exposure (24 hours)	Continuous Exposure (7 days)
Mineral Water	R	R	R
Sea Water	R	R	R
Methanol	R	NR	NR
10 % Ethanol (wine, beer)	R	R	R
96 % Ethanol (Spirit)	R	R	NR
Isopropanol (Windex)	R	R	R
Mek	R	NR	NR
Chloroform	NR	NR	NR
Methylene Chloride	NR	NR	NR
Toluene	R	R	NR
Xylene	R	R	R

* Material will stain due to exposure to these items.

R=Recommended NR=Not Recommended. Chemical Resistance determined in accordance with ASTM C267-1982.

NOTES TO SPECIFIER: Use the constant exposure recommendations for intermittent exposure to reagents at temperatures above 32°C.

Working Properties

Density— 15 lbs/gal (1.8 g/ml)

Test Standard		Temperature		
		4°C	21°C	35°C
ANSI A118.3 E-5.1	Working Time	120 min	80 min	30 min

LIL-AS-01-110904	Tack Free Time	12 hrs	4 hrs	2 hrs
LIL-AS-01-110904	Ready for Light Foot Traffic	24 hrs	12 hrs	6 hrs
LIL-AS-01-110904	Ready for Heavy Foot Traffic	48 hrs	24 hrs	12 hrs
LIL-AS-02-110904	Dirt, Stain Resistance, Food Spills, Household Cleaners	14 days	7 days	3 days
LIL-AS-03-110904	Full Cure	28 days	14 days	7 days

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

INSTALLATION

See Data Sheet 685.5, How To Install SpectraLOCK®† PRO Grout, for detailed installation instructions. This document is available online at www.laticrete.com and is included in all Part AB units.

† United States Invention Patent No.: 6881768 (and other Patents)

AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY materials are available worldwide. For distributor information, call:

Telephone: (65) 6515-3028

Fax: (65) 6515-3037

For on-line distributor information, visit LATICRETE at se.laticrete.com

Cost

Contact a LATICRETE Distributor in your area.

WARRANTY

LATICRETE International, Inc. warrants that SPECTRALOCK Pro Colour Grout is free from manufacturing defect and will not break down, deteriorate or disintegrate under normal usage for a period of one (1) year from date of purchase subject to the terms and conditions.

MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

TECHNICAL SERVICES/ CONTACT

Technical Assistance

Information is available by calling:

LATICRETE South East Asia Pte Ltd

No. 38 Sungei Kadut, Street 2

(Level 2, A3)

Singapore 729245

Telephone: (65) 6515-3028

Fax: (65) 6515-3037

Email: enquiry@laticrete.com.sg

Technical and safety literature

To acquire technical and safety literature, please visit our website at se.laticrete.com